# Indian Standard SPECIFICATION FOR BRAIDED WATER HOSE OF RUBBER, HIGH PRESSURE

(Revised)

UDC 621-643-3:678-4





© Copyright 1963 by

INDIAN STANDARDS INSTITUTION MANAK BHAVAN, 9 MATHURA ROAD NEW DELHI 1

# Indian Standard SPECIFICATION FOR BRAIDED WATER HOSE OF RUBBER, HIGH PRESSURE

(Revised)

#### Rubber Products Sectional Committee, CDC 6

Representing

DR. D. BANERJEE

National Rubber Manufacturers Ltd., Calcutta. and Association of Rubber Manufacturers in India, Calcutta

Members

MR. A. L. BLACKWOOD

Firestone Tyre & Rubber Co. of India Private Ltd., Bombay

MR. J. SAMSON ( Alternate )

SHRI P. K. BOSE

The Dunlop Rubber Co. (India) Ltd., Calcutta

SHRI J. C. SENGUPTA ( Alternate)

SHRI S. K. BOSE Government Test House, Calcutta

SHRI S. P. MULLICK ( Alternate )

MR. W. EVANS

Indian Electrical Manufacturers' Association. Calcutta

The Rubber Board, Kottayam, and The Cosmos India Rubber Works Private Ltd., Bombay

The Cosmos India Rubber Works Private Ltd.,

Indian Rubber Manufacturers' Research Associa-

Bata Shoe Co. Ltd., Calcutta
The Automotive Manufacturers' Association of

Directorate General of Armed Forces Medical

Services (Ministry of Defence)
Department of Technical Development (Ministry

of Economic & Defence Co-ordination )

SHRI D. P. SAHAI ( Alternate )

SHRI S. L. GANDHI Mit SHRI K. K. GANGULY ( Alternate ) Ministry of Defence (CGDP) Indian Rubber Manufacturers Ltd., Calcutta

MR. G. GRIFFITHS SHRI LALIT MOHAN JAMNADAS

SHRI SHAMSUNDER AZAD (Alternate)

SHRI K. V. MODAK

SHRI M. PARRAB SHRI N. M. RAJU

MAJ V. RANGANATHAN

DR. A. SEETHARAMIAH

DR. N. V. C. RAO ( Alternate ) SHRI SANJOY SEN SHRI K. R. SENGUPTA SHRI B. BASU ( Alternate )

Indian Cycle Manufacturers' Association, Calcutta Indian Rubber Industries Association, Bombay

(Continued on page 2)

STANDARDS INSTITUTION INDIAN MANAK BHAVAN, 9 MATHURA ROAD **NEW DELHI 1** 

Bombay

tion, Bombay

India, Calcutta

(Continued from page 1)

Members

DR. V. R. SHARMA

Representing

Imperial Chemical Industries (India) Private Ltd., Calcutta

DR. D. K. ROYCHAUDHURI ( Alternate )
SHRI V. S. VAIDYA Swastik
SHRI V. D. PENDSE ( Alternate ) Swastik Rubber Products Ltd., Poona

SHRI R. VENKATA RAO DR. SADGOPAL,

Railway Board (Ministry of Railways) Director, ISI ( Ex-officio Member )

Deputy Director (Chem)

Secretary

SHRI D. DAS GUPTA

Assistant Director (Chem), ISI

Hoses Subcommittee, CDC 6:3

Convener

DR. D. BANERJEE

National Rubber Manufacturers Ltd., Calcutta

Members

SHRI S. L. GANDHI

SHRI J. P. GOENKA

Ministry of Defence (CGDP)

Jaya Shree Textiles & Industries Ltd., Rishra,

Distt Hooghly

SHRI M. L. HARKAWAT ( Alternate ) SHRI K. N. KRISHNAMURTHY SHRI N. V. KRISHNAMURTHY

SHRI K. LAL ( Alternate ) SHRI LALIT MOHAN JAMNADAS ESSO Standard Eastern Incorporated, Bombay The Dunlop Rubber Co. (India) Ltd., Calcutta

The Cosmos India Rubber Works Private Ltd., Bombay

SHRI SHAMSUNDER AZAD ( Alternate )

SHRI V. N. MAKAR

SHRI LALIT MOHAN JAMNADAS (Alternate)

SHRIS. P. MULLICK

SHRI R. NAGCHAUDHRI

Indian Rubber Industries Association, Bombay

Government Test House, Calcutta

MR. R. A. BAUER ( Alternate ) DR. N. V. C. RAO

The Goodyear India Ltd., Calcutta

SHRI B. N. SETHI ( Alternate ) SHRIT. R. RAO

Department of Technical Development (Ministry of Economic & Defence Co-ordination )

SHRI H. N. DEOGAN ( Alternate

Burmah-Shell Oil Storage & Distributing Co. of India Ltd., Bombay

SHRI K. G. UNNITHAN

The Travancore Rubber Works, Trivandrum

### Indian Standard

# SPECIFICATION FOR BRAIDED WATER HOSE OF RUBBER, HIGH PRESSURE

(Revised)

#### O. FOREWORD

- 0.1 This revised Indian Standard was adopted by the Indian Standards Institution on 1 April 1963, after the draft finalized by the Rubber Products Sectional Committee had been approved by the Chemical Division Council.
- 0.2 This standard was first published in 1958. In view of the adoption of metric system in the country, the Rubber Products Sectional Committee decided to replace the existing sizes of rubber hoses by rationalized metric sizes. It was, therefore, considered necessary to revise this standard. In this revised standard rationalized metric sizes have been adopted; requirements for tensile strength and accelerated ageing, thickness of lining and cover have been modified to represent the quality of rubber products generally in demand in the country and for export trade; and the requirement for permanent set has been deleted.
- 0.3 Taking into consideration the views of producers, consumers and technologists, the Sectional Committee responsible for the preparation of this standard felt that it should be related to the prevailing manufacturing and trade practices in the country in this field. Furthermore, due consideration had been given to the need for international co-ordination among standards prevailing in different countries of the world in this field. These considerations led the Sectional Committee to consult B.S. 796:1955 Specification for Hose of Rubber with Cotton or Rayon Braided Reinforcements.
- 0.4 Wherever a reference to any Indian Standard appears in this specification, it shall be taken as a reference to the latest version of the standard.
- 0.5 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS: 2-1960 Rules for Rounding Off Numerical Values (Revised). The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

#### IS: 913 - 1963

0.6 This standard is intended chiefly to cover the technical provisions relating to braided water hose of rubber, high pressure, and it does not include all the necessary provisions of contract.

#### 1. SCOPE

1.1 This standard prescribes the requirements and the methods of sampling and test for water hose of rubber, high pressure, with braided cotton reinforcement used for car washing and spraying of mild solutions of insecticides not containing oils or tarry matter.

Note — Rayon, nylon, or any other equivalent yarns may be used for reinforcement provided test requirements specified in this standard are complied with.

#### 2. TERMINOLOGY

2.1 For the purpose of this standard the definitions given under 2 of IS: 443-1963 Methods of Sampling and Test for Rubber Hoses (Revised) shall apply.

#### 3. SAMPLING AND CRITERIA FOR CONFORMITY

3.1 For the purpose of ascertaining the conformity of the hose in a consignment to this specification, the scale of sampling and the criteria for conformity shall be as prescribed under 3 of IS: 443-1963 Methods of Sampling and Test for Rubber Hoses ( Revised ).

#### 4. CONSTRUCTION

- 4.1 The hose shall be constructed as specified in 4.1.1 to 4.1.3.
- 4.1.1 Inner Rubber Lining The inner rubber lining shall be seamless, reasonably uniform and free from air blisters, porosity and other surface defects.
- 4.1.2 Reinforcement The reinforcement shall consist of plies of cotton yarn (see under 1.1) firmly braided over the rubber lining. The plies of braid shall be so impregnated with a rubber compound that a distinct layer of rubber as braid insulation is formed between each ply.
- 4.1.3 Outer Rubber Cover The outer rubber cover shall be reasonably uniform and free from air blisters, porosity and other surface defects. The cover of the moulded type hose shall be smooth or fluted, as required. The cover of the braided hose manufactured on mandrels

shall have a cloth-marked finish, and the whole shall be consolidated by wrapping and uniformly vulcanized.

#### 5. DIMENSIONS AND TOLERANCES

5.1 Diameters and Number of Plies — The internal and external diameters of the hose and the number of reinforcement plies shall be as given in Table I.

TABLE I INTERNAL AND EXTERNAL DIAMETERS AND NUMBER OF PLIES OF BRAIDED WATER HOSE OF RUBBER, HIGH PRESSURE

SL No.	INTERNAL DIAMETER	TOLERANCE ON INTERNAL DIAMETER	MINIMUM NUMBER OF PLIES	*EXTERNAL DIAMETER	TOLERANCE ON EXTERNAL DIAMETER
(1)	(2)	(3)	(4)	(5)	(6)
	mm	mm		mm	mm
i)	10.00	±0.75	2	21.5	±1.0
ii)	12.50	±0.75	2	24.0	±1.0
iii)	16.00	±0.75	2	27.5	±1.0
iv)	20.00	±0.75	2	31.2	±1.0
v)	25.0	±1.0	3	41.0	±1.5
vi)	31.5	±1.0	3	47.5	±1.5
vii)	38.0	±1.5	3	54.0	±1.5

<sup>\*</sup>In the case of fluted hoses, this measurement shall be taken on the top of the flutes and the depth of the flute shall not exceed 0.5 mm.

<sup>5.1.1</sup> The diameters shall be measured by the method prescribed under 9 of IS: 443-1963 Methods of Sampling and Test for Rubber Hoses ( Revised ).

<sup>5.2</sup> Thickness of Lining and Cover — The thickness of the lining and cover shall be not less than that specified in Table II. The braids shall be separated by a distinct layer of rubber insulation.

<sup>5.2.1</sup> The thickness shall be measured by the method prescribed under 8 of IS: 443-1963 Methods of Sampling and Test for Rubber Hoses (Revised).

<sup>5.3</sup> Length — The standard length of the wrapped type hose shall be 15 metres. The long-length moulded-type hose shall be supplied in coils of 150 metres standard length for sizes up to and

# TABLE II THICKNESS OF LINING AND COVER OF BRAIDED WATER HOSE OF RUBBER, HIGH PRESSURE

(Clause 5.2)

SL	INTERNAL DIAMETER	THICKNESS	
No.		Lining	Cover
(1)	(2)	(3)	(4)
	mm	mm	mm
i)	10.00	2.0	1.5
ii)	Over 10:00 up to and including 20:00	2.5	1.5
iii)	Over 20:00	3.0	2.0

including 25.0 mm internal diameter and 75 metres standard length for sizes over 25.0 mm internal diameter.

Note — A coil of the moulded type hose of size up to and including 25.0 mm internal diameter may consist of not more than three lengths, no one length of which shall be less than 15 metres. A coil of hose size over 25.0 mm internal diameter may consist of not more than two lengths, no one length of which shall be less than 15 metres.

#### 6. TESTS

- 6.0 Unless otherwise agreed to between the purchaser and the supplier, all tests shall be carried out within three months of the date of receipt of the material by the purchaser.
- 6.1 Tensile Strength and Elongation at Break of Lining and Cover When tested according to the method prescribed under 4 of IS: 443-1963 Methods of Sampling and Test for Rubber Hoses (Revised), the tensile strength and elongation at break of the rubber used for the lining and cover of the hose shall be as specified in Table III.

## TABLE III TENSILE STRENGTH AND ELONGATION AT BREAK OF LINING AND COVER OF BRAIDED WATER HOSE OF RUBBER, HIGH PRESSURE

SL No.	CHARACTERISTIC	REQUIREMENT	
		Lining	Cover
(1)	(2)	(3)	(4)
		mm	mm
i)	Tensile strength, kg/cm², Min	70	70
ii)	Elongation at break, percent, Min	250	250

- 6.2 Adhesion When tested according to the method prescribed under 6 of IS: 443-1963 Methods of Sampling and Test for Rubber Hoses (Revised), the adhesion shall be such that the rate of separation does not exceed 25 mm per minute under a load of 4.5 kg for the following:
  - a) Between braids,
  - b) Between lining and braid, and
  - c) Between cover and braid.
- 6.3 Accelerated Ageing Test After ageing as prescribed under 7 of IS: 443-1963 Methods of Sampling and Test for Rubber Hoses (Revised), the tensile strength and elongation at break of the rubber used for the lining and cover of the hose shall not vary by more than ±35 percent of the corresponding value obtained before ageing.
- 6.4 Hydraulic Test When tested according to the method prescribed under 11 of IS: 443-1963 Methods of Sampling and Test for Rubber Hoses (*Revised*), the hose shall comply with the requirements specified in Table IV.
- 6.4.1 The recommended working pressure shall be one-fourth of the minimum bursting pressure specified in Table IV.

TABLE IV REQUIREMENTS FOR HYDRAULIC TEST FOR BRAIDED WATER HOSE OF RUBBER, HIGH PRESSURE

SL No.	INTERNAL DIAMETER	REQUIREMENT		
No.		Increase in External Diameter Under Pressure of 20.0 kg/cm², Percent, Max	Bursting Pressure kg/cm², Min	
(1)	(2)	(3)	(4)	
	mm			
i)	10.00	7	85	
ii)	12.50	7	85	
iii)	16.00	7	70	
iv)	20.00	7	70	
v)	25.0	10	50	
vi)	31.5	10	40	
vii)	38.0	10	35	

IS: 913 - 1963

#### 7. MARKING

- 7.1 Each length of the wrapped type hose shall be indelibly marked adjacent to each end with:
  - a) the manufacturer's name or trade-mark and hose denominations; and
  - b) the month and year of manufacture, if required by the purchaser.
- 7.2 For long-length moulded type hose, the markings specified under 7.1 shall be made at intervals of 10 metres.
- 7.3 Each length of the hose of both wrapped and moulded types may also be marked with the ISI Certification Mark.

NOTE — The use of the ISI Certification Mark is governed by the provisions of the Indian Standards Institution (Certification Marks) Act, and the Rules and Regulations made thereunder. Presence of this mark on products coveredby an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that Standard, under a well-defined system of inspection, testing and quality control during production. This system, which is devised and supervised by ISI and operated by the producer, has the further safeguard that the products as actually marketed are continuously checked by ISI for conformity to the Standard. Details of conditions, under which a licence for the use of the ISI Certification Mark may be granted to manufacturers or processors, may be obtained from the Indian Standards Institution.