IS : 5166 - 1969

Indian Standard

SPECIFICATION FOR CEMENT GROUTING HOSE OF RUBBER WITH BRAIDED TEXTILE REINFORCEMENT

UDC 621.643.3:678.4:693.546.3



© Copyright 1969

INDIAN STANDARDS INSTITUTION
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 1

Indian Standard

SPECIFICATION FOR CEMENT GROUTING HOSE OF RUBBER WITH BRAIDED TEXTILE REINFORCEMENT

Rubber Products Sectional Committee, CDC 6

Representing

DR D. BANERJEE

National Rubber Manufacturers Ltd, Calcutta; and Association of Rubber Manufacturers of India, Calcutta

Members

DR B. B. BHATIA

I. C. I. (India) Private Ltd, Calcutta

SHRI D. K. CHATTERJEE (Alternate)
SHRI S. K. BOSE
National Test House, Calcutta

SHRI A. GHOSH (Alternate) SHRI DALIP KUMAR

Railway Board (Ministry of Railways)
Export Inspection Council of India, Calcutta

SHRI G. C. DE Export SHRI P. K. CHATTERJEE (Alternate)

Ministry of Defence (DGI)

SHRI S. L. GANDHI M SHRI B. H. DALAL (Alternate)

Ministry of Defence (R & D)

SHRI B. H. DARAY Ministry of Dolons Shri K. K. GANGULY Ministry of Dolons Shri N. S. BANKER (Alternate)

Rubber Board, Kottayam

Rubber Stael Ltd. Ranc

SHRI G. C. JAIN SHRI S. R. KOCHHAR Hindustan Steel Ltd, Ranchi

Inspection Wing, Directorate General of Supplies & Disposals, New Delhi
The Cosmos India Rubber Works Private Ltd,

SHRI LALIT MOHAN JAMNADAS

Bombay

SHRI PULIN L. KINARIWALA (DR K. N. MODAK

Alternate |
Indian Rubber Manufacturers Research Association, Bombay; and Indian Rubber Industries
Association, Bombay

SHRI K. R. SENGUPTA (Alternate)
SHRI S. MUKHERJEE

The Dunlop India Ltd, Calcutta

SHRI G. P. DUTTA (Alternate SHRI S. C. NANDY SHRI M. M. PATEL

DR A. SEETHARAMIAH

Bata Shoe Co Private Ltd, Calcutta Synthetics and Chemicals Ltd, Bombay Directorate General of Technical Development,

Indian Rubber Industries Association, Bombay

New Delhi

DR N. V. C. RAO (Alternate)

(Continued on page 2)

INDIAN STANDARDS INSTITUTION MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG **NEW DELHI 1**

IS: 5166 - 1969

SHRI A. R. YAJNIK

(Continued from page 1) Representing Members All India Automobile & Ancillary Industries SHRI D. D. TALWALKAR Association, Bombay SHRI R. M. KHALADKAR (Alternate) Indian Oil Corporation Ltd (Marketing Division), SHRI A. R. YAJNIK Bombay SHRI M. K. JAIN (Alternate) Director General, ISI (Ex-officio Member) SHRI D. DAS GUPTA, Director (Chem) Secretary SHRI N. R. SRINIVASAN Deputy Director (Chem), ISI Hoses Subcommittee, CDC 6:3 Convener National Rubber Manufacturers Ltd, Calcutta DR D. BANERJEE Members Ministry of Defence (DGI) SHRI S. L. GANDHI Shri B. H. Dalal (Alternate)
Shri B. C. Jain
Shri A. K. Ghosh (Alternate)

Shri A. K. Ghosh (Alternate)

Shri A. K. Ghosh (Alternate) The Cosmos India Rubber Works Private Ltd, SHRI LALIT MOHAN JAMNADAS Bombay SHRI S. G. JAMBHEKAR (Alternate)

SHRI S. KRISHNASWAMY

Esso Standard Eastern Inc., Bombay SHRI M. S. KRISHNASWAMY SHRI A. V. SUNDERARAMAN Alternate)
Dunlop India Ltd, Calcutta SHRI K. LAL SHRI C. S. MANI (Alternate) Indian Rubber Industries Association, Bombay SHRI LALIT MOHAN JAMNADAS (Alternate)
SHRI S. P. MULLICK National Test House, Calcutta
SHRI R. NAGCHAUDHURI Goodyear India Ltd, Calcutta SHRI S. R. GANGULI (Alternate)
SHRI M. M. PATEL
Sy Synthetics and Chemicals Ltd, Bombay Swastik Rubber Products Ltd, Poona SHRI V. D. PENDSE SWASHI SHRI D. D. TALWALKAR (Alternate) DR N. V. C. RAO Directo Directorate General of Technical Development, New Delhi East India Rubber Works Private Ltd, Calcutta Indian Oxygen Ltd, Calcutta SHRI G. R. INAMDAR (Alternate) SHRI B. ROY SHRI S. V. SAMBAMURTI Burmah-Shell Oil Storage & Distributing Co of India Ltd, Bombay
Indian Oil Corporation Ltd (Marketing SHRI S. S. MAZUMDAR (Alternate) SHRI K. S. SUBBANNA

Division), Bombay

Indian Standard

SPECIFICATION FOR CEMENT GROUTING HOSE OF RUBBER WITH BRAIDED TEXTILE REINFORCEMENT

0. FOREWORD

- 0.1 This Indian Standard was adopted by the Indian Standards Institution on 23 May 1969, after the draft finalized by the Rubber Products Sectional Committee had been approved by the Chemical Division Council.
- 0.2 These hoses are used for cement grouting purposes. Keeping the working condition in view, hoses suitable for working pressure up to 10.0 kgf/cm² have been prescribed in this standard. Recommended minimum outside diameters have been included in Appendix A for the guidance of the manufacturers and consumers.
- 0.3 The nominal bore sizes prescribed in this standard are those recommended by ISO/TC 45 Rubber of International Organization for standardization (ISO).
- 0.4 This standard contains clauses 4.2 and 6.1 which call for agreement between the purchaser and the supplier.
- 0.5 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS: 2-1960*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard prescribes the requirements, methods of sampling and test for cement grouting hose of rubber with braided textile reinforcement, and built on mandrels. The hose is designed for working pressures up to 10.0 kgf/cm².

^{*}Rules for rounding off numerical values (revised).

IS: 5166 - 1969

2. TERMINOLOGY

2.1 For the purpose of this standard, the definitions given in 2 of IS: 443-1963* shall apply.

3. REQUIREMENTS

3.1 Materials

- 3.1.1 Lining The lining shall consist of a suitable rubber compound.
- 3.1.2 Reinforcement The textile reinforcement shall consist of yarn of natural or man-made fibre.
 - 3.1.3 Cover The cover shall consist of suitable rubber compound.

3.2 Construction

- 3.2.1 Lining The lining shall be reasonably uniform in thickness, concentric and free from air blisters, porosity and splits. It shall be seamless and smooth in the bore.
- 3.2.2 Reinforcement The textile reinforcement shall be firmly and evenly braided over the lining. The plies of reinforcement shall be impregnated with a rubber compound.
- 3.2.3 Braided Copper Wire One copper wire braid comprising of number of strands and of minimum breaking load of 9 kg shall be incorporated in one of the ply to provide electrical continuity along with the whole length of the hose. In case, two copper wires are used, the minimum composite breaking load shall be 9 kg.
- 3.2.4 Cover The cover shall be reasonably uniform in thickness, concentric and free from air blisters, porosity and other visible defects. The cover of the braided hose manufactured on mandrels may have a cloth marked finish and the whole shall be consolidated by wrapping and uniformly vulcanized.

3.3 Dimensions and Tolerances

- 3.3.1 Bore Sizes and Number of Plies The bore sizes and tolerances shall be as given in Table 1 when measured according to the method prescribed in 9.1 of IS: 443-1963*. The minimum number of plies shall be as given in col 4 of Table 1.
- 3.3.2 Lining and Cover Thickness The thickness of the lining shall not be less than 6.3 mm and that of cover not less than 1.5 mm, when measured according to 8 of IS: 443-1963*.

^{*}Methods of sampling and test for rubber hoses (revised).

TABLE 1 BORE SIZES, TOLERANCES AND NUMBER OF REINFORCEMENT PLIES

(Clause 3.3.1)

SL No.	Nominal Bore Size	Tolerance on Nominal Bore Size	MINIMUM NUMBER OF PLIES
(1)	(2)	(3)	(4)
	mm	mm	
i)	25	± 1·25	3
ii)	31.5	± 1·25	3
iii)	38	± 1.50	3
iv)	50	± 1·50	3
V)	63	± 1·50	3
vi)	75	± 2·00	3

- 3.3.3 Length The standard length of the hose shall be 15 m.
 - 3.3.3.1 The tolerance on hose length shall be \pm 1 percent.

3.4 Requirement for Physical Characteristics on Finished Hose

3.4.1 Tensile Strength and Elongation at Break of Lining and Cover -The tensile strength and elongation at break of the rubber used for the lining and cover of the hose when determined according to the method prescribed in 4 of IS: 443-1963* shall be as specified in Table 2.

TABLE 2 TENSILE STRENGTH AND ELONGATION AT BREAK OF LINING AND COVER

SL No.	CHARACTERISTIC	REQUIREMENTS	
		Lining	Cover
(1)	(2)	(3)	(4)
i) ii)	Tensile strength, kgf/cm², Min Elongation at break, percent, Min	140 500	85 300

- 3.4.2 Hardness of Lining The international rubber hardness degrees (IRHD) of the lining shall be 50 \pm 5, when determined according to IS: 3400 (Part II)-1965†.
- 3.4.3 Accelerated Ageing Test After ageing at $70^{\circ}\text{C} \pm 1^{\circ}\text{C}$ for a period of 72 hours according to the method prescribed in IS: 3400 (Part IV)-1965; the rubber used for the lining and cover when tested

^{*}Methods of sampling and test for rubber hoses (revised).
†Methods of tests for vulcanized rubbers: Part II Hardness.

Methods of tests for vulcanized rubbers: Part IV Accelerated ageing.

IS: 5166 - 1969

according to 4 of IS: 443-1963* shall not vary by more than \pm 25 percent for tensile strength and + 10 and - 30 percent for elongation at break of the corresponding values obtained before ageing.

- 3.4.4 Adhesion The adhesion when tested according to the method prescribed in 6 of IS: 443-1963* shall be such that the rate of separation does not exceed 25 mm per minute under a load of 5.0 kg for the following:
 - a) Between reinforcement plies,
 - b) Between lining and reinforcement plies, and
 - c) Between cover and reinforcement plies.
- 3.4.5 Bursting Pressure The hose shall have a minimum bursting pressure of 40 kgf/cm² when tested according to the method prescribed in 11 of IS: 443-1963*.
- 3.4.6 Proof Pressure Test Samples of production lengths of hose shall be subjected to internal hydraulic pressure of 1.5 times the working pressure for one minute. The hose shall not show any rupture, leakage or porosity when tested according to the method prescribed in 12 of IS: 443-1963*.

Note — This test shall be carried out at the factory. If the hose is offered at places other than the factory, manufacturer's certificate shall be accepted.

3.4.7 Electrical Continuity — Each manufactured length of hose shall be tested to show evidence of electrical continuity.

Note — 4.5 V battery or transformer and a 3.5 V, 0.3 A test bulb may be used for this test.

4. MARKING AND PACKING

- 4.1 Each length of the hose shall be indelibly marked adjacent to each end with:
 - a) the manufacturers name or trade-mark, if any;
 - b) hose denomination; and
 - c) month and year of manufacture, if required by the purchaser.

^{*}Methods of sampling and test for rubber hoses (revised).

4.1.1 Each length of hose may also be marked with the ISI Certification Mark.

Note — The use of the ISI Certification Mark is governed by the provisions of the Indian Standards Institution (Certification Marks) Act, and the Rules and Regulations made thereunder. Presence of this mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard, under a well-defined system of inspection, testing and quality control during production. This system, which is devised and supervised by ISI and operated by the producer, has the further safeguard that the products as actually marketed are continuously checked by ISI for conformity to the standard. Details of conditions, under which a licence for the use of the ISI Certification Mark may be granted to manufacturers or processors, may be obtained from the Indian Standards Institution.

4.2 Packing — The material shall be packed as agreed to between the purchaser and the supplier.

5. SAMPLING AND CRITERIA FOR CONFORMITY

5.1 For the purpose of ascertaining the conformity of the hose in a consignment to this specification, the scale of sampling and the criteria for conformity shall be as prescribed in 3 of IS: 443-1963*.

6. TESTS

6.1 Unless otherwise agreed to between the purchaser and the supplier, all tests shall be carried out within three months from the date of receipt of the material by the purchaser.

APPENDIX A

(Clause 0.2)

RECOMMENDED MINIMUM OUTSIDE DIAMETER

A-1. The recommended minimum outside diameter for various bore sizes of hoses should be as given in Table 3.

	TABLE 3	RECOMMENDED MINIMU	IM OUTSIDE DIAMETER
SL No.		NOMINAL BORE SIZE	RECOMMENDED MINIMUM OUTSIDE DIAMETER
(1)		(2)	(3)
		mm	mm
i)		25	41.5
ii) ii) v)		31·5 38	51·0 57·0
v)		50	69-0
V)		63 75	82.0
vi)		75	93.5

^{*}Methods of sampling and test for rubber hoses (revised).

INDIAN STANDARDS

ON

Hoses

IS:		$\mathbf{R}\mathbf{s}$
443-1963	Methods of sampling and test for rubber hoses (revised) -	3.50
444-1968	Water hose of rubber with woven textile reinforcement (second revision) (superseding IS: 445-1964)	3.50
446-1968	Air hose of rubber with woven textile reinforcement (second revision) (superseding IS: 3557-1965)	3.50
447-1968	Welding hose of rubber with woven textile reinforcement (second revision)	3.50
635-1968	Oil and solvent resistant hose of rubber with woven textile reinforcement (second revision)	2.50
636-1962	Fire fighting hose (rubber lined woven-jacketed) (revised)	2.50
911-1968	Air hose of rubber with braided textile reinforcement (second revision) (superseding IS: 912-1963)	3.50
913-1968	Water hose of rubber with braided textile reinforcement (second revision) (superseding) 18:914-1963)	3.50
1677-1968	Agricultural spray hose of rubber with braided textile reinforcement (second revision)	3.20
2396-1968	Rubber hose for petrol and diesel fuels with braided textile reinforcement (first revision) (under print)	
2410-1963	Suction hose of rubber for hire services	1.50
2482-1963	Water suction hose of rubber, light duty	1.50
2765-1964	Radiator hose	2.50
3418-1968	Oil and solvent resistant hose of rubber with braided textile reinforcement (first revision)	2.50
3549-1965	Water suction and discharge hose of rubber, heavy duty	1.50
3572-1968	Welding hose of rubber with braided textile reinforcement (first revision)	2.50
3692-1965	Rubber closures (pharmaceuticals)	3.00
5137-1969	Cement grouting hose of rubber with woven textile reinforcement	2.50
5166-1969	Cement grouting hose of rubber with braided textile rein- forcement	2.50