

IS : 7351 - 1985

Indian Standard
SPECIFICATION FOR
STYRENATED PHENOL
(*First Revision*)

UDC 678.4.048 : 547.562.1



© Copyright 1986

INDIAN STANDARDS INSTITUTION
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

Gr 3

January 1986

IS : 7351 - 1985

Indian Standard
SPECIFICATION FOR
STYRENATED PHENOL
(*First Revision*)

Rubber Products Sectional Committee, PCDC 13

Chairman

DR D. BANERJEE

Representing

Escon Consultants Pvt Ltd, Calcutta

Members

SHRI M. L. BAHRANI	Ministry of Defence (R & D)
SHRI RAJINDRA SINGH (<i>Alternate</i>)	
DR B. BANERJEE	Carbon & Chemicals India Ltd, Cochin
DR P. S. BHARGAVA	Alkali & Chemical Corporation of India Ltd, Rishra
SHRI N. C. SAMAJDAR (<i>Alternate</i>)	
DR S. N. CHAKRAVARTY	Modi Rubber Ltd, Modipuram
SHRI L. K. MATHUR (<i>Alternate</i>)	
SHRI J. CHATTERJEE	Andrew Yule & Co Ltd, Calcutta
SHRI A. K. BISWAS (<i>Alternate</i>)	
SHRI P. B. G. DASTIDAR	Bata India Ltd, Calcutta
SHRI SUNIL SARKAR (<i>Alternate</i>)	
SHRI W. G. DESAI	All India Rubber Industries Association, Bombay
SHRI R. R. PANDIT (<i>Alternate</i>)	
SHRI B. DUTTA	Bengal Waterproof Ltd, Calcutta
SHRI R. N. WAHIE (<i>Alternate</i>)	
SHRI S. B. GANGULY	Dunlop India Ltd, Calcutta
SHRI T. V. RAMACHANDRAN (<i>Alternate</i>)	
SHRI J. M. GARG	Directorate General of Technical Development, New Delhi
SHRI A. GHOSH	National Test House, Calcutta
SHRI LALIT MOHAN JAMNADAS	Cosmos India Rubber Works Pvt Ltd, Bombay
SHRI P. L. KINARIWALA (<i>Alternate</i>)	
SHRI S. V. LATHIA	Lathia Rubber Manufacturing Co Pvt Ltd, Bombay
SHRI V. S. LATHIA (<i>Alternate</i>)	
SHRI A. K. MALLIK	Indian Petrochemicals Corporation Ltd, Vadodara
SHRI R. S. PATEL (<i>Alternate</i>)	
DR S. P. MANIK	Research, Designs and Standards Organization, Lucknow
DEPUTY DIRECTOR (STAT) (MP) (<i>Alternate</i>)	

(*Continued on page 2*)

© Copyright 1986

INDIAN STANDARDS INSTITUTION

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

IS : 7351 - 1985

(Continued from page 1)

<i>Members</i>	<i>Representing</i>
SHRI C. K. MEHROTRA	Export Inspection Council of India, Calcutta
SHRI S. S. CHOPRA (Alternate)	
DR R. N. MEHROTRA	Synthetics and Chemicals Ltd, Bombay
SHRI P. F. MILLER	Directorate General of Supplies & Disposals, New Delhi
SHRI S. C. KOHLI (Alternate)	
DR W. MILLNS	Indian Rubber Manufacturers Research Association, Thane
DR M. S. BANERJI (Alternate)	
SHRI N. NAGARAJAN	Sundram Industries Pvt Ltd, Madurai
SHRI P. VIJAYARAGHAVAN (Alternate)	
SHRI R. R. PANDIT	Bayer (India) Ltd, Bombay
SHRI D. J. BHARUCHA (Alternate)	
SHRI K. S. RADHAKRISHNAN	National Rubber Manufacturers Ltd, Calcutta
SHRI R. P. MATHUR (Alternate)	
SHRI M. B. RAMGARDIA	Indian Oil Corporation Ltd, Bombay
SHRI J. M. SINGH (Alternate)	
SHRI B. C. SEN	Ministry of Defence (DGI)
SHRI V. BHATTACHARYA (Alternate)	
SHRI E. V. THOMAS	Rubber Research Institute of India, Kottayam
DR M. G. KUMARAN (Alternate)	
DR G. T. VERGHESE	J. K. Industries Ltd, New Delhi
SHRI RAVI JAIN (Alternate)	
SHRI M. S. SAXENA, Director (P&C)	Director General, ISI (Ex-officio-Member)

Secretary

SHRI AMARJIT SINGH
Assistant Director (P&C), ISI

**Rubber Chemicals & Compounding Ingredients Subcommittee,
PCDC 13 : 5**

Convener

SHRI S. B. GANGULY Dunlop India Ltd, Calcutta

Members

SHRI A. SEN (Alternate to Shri S. B. Ganguly)	
SHRI A. K. BANDYOPADHYA	Ministry of Defence (DGI)
SHRI P. L. NAG (Alternate)	
DR M. C. BADRINARAYANA	Bayer (India) Limited, Bombay
SHRI R. R. PANDIT (Alternate)	
DR B. BANERJEE	Carbon and Chemicals India Ltd, Cochin
DR P. S. BHARGAVA	Alkali and Chemical Corporation of India Ltd, Rishra
DR S. K. KAPOOR (Alternate)	

(Continued on page 11)

Indian Standard
SPECIFICATION FOR
STYRENATED PHENOL
(First Revision)

0. FOREWORD

0.1 This Indian Standard (First Revision) was adopted by the Indian Standards Institution on 27 March 1985, after the draft finalized by the Rubber Products Sectional Committee had been approved by the Petroleum, Coal and Related Products Division Council.

0.2 This standard was originally published in 1974. In this revision, the requirements of refractive index and relative density have been modified.

0.3 Styrenated phenols are non-staining and non-discolouring antioxidants finding application in white and transparent vulcanizates. In this standard the requirements pertaining to the product obtained by arylating phenol with styrene only is considered. This is essentially a mixture of mono-, di- and tri-styrenated phenol with molecular mass ranging from 200 to 400. This product is soluble in benzene, acetone, ethyl alcohol and petroleum ether and insoluble in water.

0.4 Besides specifying chemical requirements, the standard includes a recommended procedure for evaluating the material by means of a standard compounding and vulcanizing procedure.

0.5 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS : 2-1960*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard prescribes the requirements and methods of sampling and test for styrenated phenol intended for use as an antioxidant in rubber compounds.

*Rules for rounding off numerical values (revised).

IS : 7351 - 1985

2. REQUIREMENTS

2.1 Description — The material shall be in the form of a clear viscous liquid not darker than pale amber colour. It shall not contain any visible impurities.

2.2 The material shall comply with the requirements given in Table 1 when tested according to the methods given in Appendix A. Reference to the relevant clauses of Appendix A is given in col 4 of Table 1.

TABLE 1 REQUIREMENTS FOR STYRENATED PHENOL

Sl. No.	CHARACTERISTIC	REQUIREMENT	METHOD OF TEST (REF TO CL No. IN APPENDIX A)
(1)	(2)	(3)	(4)
i)	Refractive index at 27°C	1.595 0 to 1.605 0	A-2
ii)	Relative density at 27°C/ 27°C	1.079 to 1.085	A-3
iii)	Viscosity at 27°C, CPS	2 000 to 6 000	A-4
iv)	Acidity (as H_2SO_4), per- cent by mass, <i>Max</i>	0.1	A-5
v)	Ash, percent by mass, <i>Max</i>	0.1	A-6
vi)	Flash point in °C, <i>Min</i>	120	A-7
vii)	Volatile matter at 60°C, percent by mass, <i>Max</i>	1.0	A-8

2.2.1 All the tests shall be carried out within one month of receipt of the material by the purchaser.

2.3 Compounding — The material when compounded and tested as given in Appendix B shall have its performance comparable with that of a sample, previously approved by the purchaser complying with the requirements given in 2.1 and 2.2.

3. PACKING AND MARKING

3.1 Packing — The material shall be packed in 25 kg and 200 kg drums or as agreed to between the purchaser and the supplier.

3.2 Marking — The packages shall be securely sealed and legibly marked with the following information:

- Manufacturer's name and registered trade-mark, if any;
- Chemical name or trade name of the material;
- Net mass of the package; and
- The lot and the batch number.

IS : 7351 - 1985

3.2.1 The packages may also be marked with the ISI Certification Mark.

NOTE — The use of the ISI Certification Mark is governed by the provisions of the Indian Standards Institution (Certification Marks) Act and the Rules and Regulations made thereunder. The ISI Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well-defined system of inspection, testing and quality control which is devised and supervised by ISI and operated by the producer. ISI marked products are also continuously checked by ISI for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the ISI Certification Mark may be granted to manufacturers or processors, may be obtained from the Indian Standards Institution.

4. SAMPLING AND CRITERIA FOR CONFORMITY

4.1 Sampling

4.1.1 Lot — All the containers in a single consignment manufactured under the same condition shall constitute a lot.

4.1.2 Samples shall be tested for each lot separately for ascertaining the conformity of the material to the requirements of the specification.

4.1.3 The number of containers to be chosen from the lot shall be in accordance with Table 2.

TABLE 2 SCALE OF SAMPLING

LOT SIZE	NO. OF CONTAINERS TO BE CHOSEN
Up to 50	3
51 to 100	4

A P P E N D I X A

(Table 1)

TEST METHODS FOR STYRENATED PHENOL

A-1. QUALITY OF REAGENTS

A-1.1 Unless specified otherwise, pure chemicals and distilled water (see IS : 1070-1977*) shall be employed in the tests.

NOTE — 'Pure chemicals' shall mean chemicals that do not contain impurities which affect the results of test or analysis.

*Specification for water for general laboratory use (second revision).

IS : 7351 - 1985

A-2. DETERMINATION OF REFRACTIVE INDEX

A-2.1 Apparatus

A-2.1.1 Abbe-refractometer of standard make covering a range of 1.300 to 1.700 suitable for reading up to fourth place of decimal and provided with thermostat.

A-2.2 Procedure

A-2.2.1 Start the thermostat attached to the apparatus and wait till it attains a constant temperature at $27.0 \pm 0.5^{\circ}\text{C}$. Clean the prism with cotton soaked with alcohol and wait till alcohol is evaporated off.

A-2.2.2 Transfer a drop of styrenated phenol on the prism with the help of a clean, dry glass rod and close the prism carefully. Adjust the eye piece in such a manner that the cross wires coincide with the line of demarcation between bright and dark region. Read the result on the dial to fourth place of decimal with the help of the vernier scale.

A-2.3 Precautions

- a) Check occasionally the readings of the instrument with test sample;
- b) Temperature should be controlled within the limit of $\pm 1^{\circ}\text{C}$;
- c) Clean the prism with alcohol;
- d) Put right quantity of liquid on the prism; and
- e) There should be no air bubble in the sample while taking reading.

A-3. DETERMINATION OF RELATIVE DENSITY

A-3.1 Apparatus

A-3.1.1 *Hydrometer* — with a range of 1.000 to 1.110.

A-3.1.2 *Measuring Cylinder*— 100-ml. Internal diameter 28 mm and internal height 250 mm.

A-3.1.3 *Thermostat*

A-3.2 Procedure — Fill styrenated phenol in a clean, dry, measuring cylinder to 100 ml mark (approximately) and place the cylinder in a thermostat. Start the thermostat and wait till it attains a constant temperature at $27 \pm 1^{\circ}\text{C}$. Check that the material has also attained the set temperature. Now allow the clean, dry, hydrometer to be immersed in the liquid and wait till it assumes a steady position. The reading corresponding to the meniscus of the liquid will give the relative density of the sample.

A-3.3 Precautions

- a) Avoid any entrapment of air bubbles in the samples;
- b) Take care that the hydrometer does not touch the cylinder wall, and
- c) While taking reading, position of eye should be on the same level as of the meniscus.

A-4. DETERMINATION OF VISCOSITY

A-4.0 General — The measurement of the drag produced upon a given spindle rotating at a definite constant speed while immersed in the material at a given temperature and indicated on a dial produces viscosity readings in centipoise.

A-4.1 Apparatus

A-4.1.1 Brook Field Synchro Electric Viscometer.

A-4.2 Procedure

A-4.2.1 Support the viscometer on the stand and level. Attach spindle No. 3 by holding the upper shaft coupling and turning the spindle. Place sample in as wide a container as possible that will give the proper depth and adjust to $27 \pm 1^\circ\text{C}$. Lower the instrument so that the spindle is immersed in the liquid to the groove on the spindle. Check levelling and centre spindle by moving container. Set hexagonal knob to the proper speed (rpm) and start motor by snapping toggle switch.

A-4.2.2 After 8 to 10 revolutions press down clutch level on the back and shut off motor so that the dial indicator is visible. Keep clutch level depressed to hold the reading. Without releasing the clutch start motor first and then release the clutch. After the second 8 to 10 revolutions, repeat the steps above to get the check reading. Make several check readings, allowing enough time to attain shear equilibrium between readings. Release clutch after shutting off motor and while spindle is still immersed raise instrument and remove spindle carefully by holding the upper shaft coupling firmly.

Factor for spindle at different speeds:

<i>RPM</i>	<i>Spindle No. 3</i>
60	20
30	40
12	100
6	200

Deduct 8 cps from final reading as drag correction.

IS : 7351 - 1985

A-5. DETERMINATION OF ACIDITY

A-5.0 General — This method determines the acidity in styrenated phenol. The result is expressed in terms of percent sulphuric acid.

A-5.1 Reagents

A-5.1.1 Methanol

A-5.1.2 Potassium Hydroxide Solution — 0.5 N, alcoholic.

A-5.1.3 Phenolphthalein Indicator

A-5.2 Procedure — Weigh 100 g of styrenated phenol to the nearest mg in a one litre conical flask and dissolve the contents in 500 ml of methanol thoroughly. Titrate the solution with 0.5 N alcoholic potassium hydroxide using phenolphthalein as indicator.

A-5.3 Calculation

Acidity (as H_2SO_4), percent = $0.0245 \times \text{ml of } 0.5 \text{ N}$
by mass potassium hydroxide

A-6. DETERMINATION OF ASH CONTENT

A-6.1 Procedure

A-6.1.1 Heat a clean, dry, silica crucible to $550 \pm 25^\circ\text{C}$ for 30 minutes. Cool in a desiccator and weigh it to the nearest mg. In the crucible weigh to the nearest 0.001 g about 10 g of a representative sample of the material under test.

A-6.1.2 Place the crucible in the hole in the asbestos board, place the board on a tripod stand and heat the crucible from below with a Bunsen flame. Heat gently, avoiding ignition until the sample has all volatilised, pyrolyzed or charred. Transfer the crucible to the muffle furnace at $550 \pm 25^\circ\text{C}$ and leave for 30 minutes or longer until all the carbon has burnt off. Remove from the furnace, cool to room temperature in a desiccator and weigh to the nearest 0.001 g.

A-6.1.3 Calculation

Ash, percent by mass = $\frac{B - A}{M} \times 100$

where

A = mass in g of the crucible;

B = mass in g of the crucible plus ash; and

M = mass in g of the sample.

A-7. DETERMINATION OF FLASH POINT

A-7.1 Procedure — Flash point determination is carried out by the Pensky-Marten closed cup method as indicated in **A-7-1.1**.

A-7.1.1 Thoroughly clean the cup and accessories taking care to remove any gasoline or naphtha used for cleaning. Fill the cup to the filling mark with the styrenated phenol. After locking in the lid properly, place the cup on the stove. Light the test flame, adjust it to 4 mm diameter. Rate of heating should be such that there is 60°C temperature rise per minute. The stirrer should run at 90 to 120 rpm. Apply test flame at 104°C by operating the mechanism on the cover which controls the shutter and test flame burner so that the flame lowered into the vapour space of the cup in one second, left in its lowered position for one second and quickly raised to its high position. Continue to apply the flame after every 20°C rise in temperature till the flash point is reached. Flash point temperature is the temperature at which the test flame application cause a distinct flash in the interior of the cup.

A-8. DETERMINATION OF VOLATILE MATTER

A-8.1 Weigh 50 g of the styrenated phenol in a previously weighed evaporation dish. Keep the dish in vacuum at 60°C and pressure of 40 mm of mercury for 2 hours. Record the loss in mass.

Volatile matter, percent by mass = $2 \times \text{loss in mass}$.

A P P E N D I X B

(Clause 2.3)

**METHOD OF COMPOUND TESTING OF
STYRENATED PHENOL****B-1. TEST COMPOUND**

B-1.1 As a guidance, the following test compound may be used for testing performance properties of styrenated phenol in rubber compounds:

	<i>Parts by Mass</i>
Natural rubber grade A (<i>see</i> IS : 4588-1977*)	100
Barytes (<i>see</i> IS : 1683-1973†)	60
Zinc oxide (<i>see</i> IS : 3399-1973‡)	10

*Specification for rubber, raw natural (*second revision*).

†Specification for barytes for rubber industry (*first revision*).

‡Specification for zinc oxide for rubber industry (*first revision*).

IS : 7351 - 1985

	<i>Parts by Mass</i>
Stearic acid (<i>see</i> IS : 1675-1971*)	0.5
Titanium dioxide (<i>see</i> IS : 8862-1978†)	10
Antioxidant styrenated phenol	2.0
Sulphur (<i>see</i> IS : 8851-1978‡)	2.0
Tetramethyl thiuram disulphide (<i>see</i> IS : 8979-1978§)	0.5

B-2. PROCEDURE

B-2.1 Follow the procedure prescribed in NR : 9 of IS : 3660 (Part 1)-1972||.

B-3. TESTS

B-3.1 The test given below is recommended for each test sample. The approved sample shall also be tested side by side using the same master batch.

B-3.2 Tensile strength, modulus at 300 percent elongation, elongation at break and hardness at optimum cure at 141°C shall be carried out in accordance with the method prescribed in the appropriate parts of IS : 3400¶ both before and after ageing at 70°C for 7 days.

B-4. RESULTS

B-4.1 The tensile strength, modulus at 300 percent elongation and elongation at break, both of the original sample and the tested aged sample shall be within ± 10 percent of the approved sample tested at the same time.

*Specification for stearic acid, technical (*first revision*).

†Specification for titanium dioxide (anatase type) for rubber industry.

‡Specification for sulphur for rubber industry.

§Specification for tetra methyl thiuram disulphide.

||Methods of test for natural rubber, Part 1

¶Methods of test for vulcanized rubber.

(Continued from page 2)

<i>Members</i>	<i>Representing</i>
SHRI B. BHATTACHARYA	Incheck Tyres Ltd, Calcutta
SHRI P. K. SARKAR (<i>Alternate</i>)	
DR S. N. CHAKRAVARTY	Modi Rubber Ltd, Modipuram
SHRI L. K. MATHUR (<i>Alternate</i>)	
SHRI J. CHATTERJEE	Andrew Yule & Co Ltd, Calcutta
SHRI A. K. BISWAS (<i>Alternate</i>)	
DR D. K. DAS	National Test House, Calcutta
SHRI P. B. G. DASTIDAR	Bata India Ltd, Calcutta
SHRI S. SARKAR (<i>Alternate</i>)	
SHRI R. W. DHARWADKAR	United Carbon India Ltd, Bombay
SHRI J. N. GHOSAL	Sturdia Chemical Ltd, Bombay
SHRI H. S. VIJAYANATH (<i>Alternate</i>)	
SHRI A. M. KAPOOR	Rishiroop Polymers Pvt Ltd, Bombay
SHRI K. J. JACOB (<i>Alternate</i>)	
SHRI PULIN L. KINARIWALA	Cosmos India Rubber Works Pvt Ltd, Bombay
SHRI S. N. GHADGE (<i>Alternate</i>)	
SHRI R. P. MATHUR	National Rubber Manufacturers Ltd, Calcutta
SHRI A. K. BISWAS (<i>Alternate</i>)	
DR R. N. MEHROTRA	Synthetics and Chemicals Ltd, Bombay
DR B. SURYANARAYANAN (<i>Alternate</i>)	
SHRI S. M. MEHTA	Camphor & Allied Products Ltd, Bareilly
SHRI S. N. MEHRA (<i>Alternate</i>)	
DR W. MILLNS	Indian Rubber Manufacturers Research Association, Thane
SHRI N. B. FEGADE (<i>Alternate</i>)	
DR D. K. PATEL	Nirlon Synthetic Fibres & Chemicals Ltd, Bombay
SHRI A. K. SEN CHAUDHURI (<i>Alternate</i>)	
SHRI V. D. PENDSE	Swastic Rubber Products Ltd, Pune
SHRI S. V. TATHWADKAR (<i>Alternate</i>)	
SHRI P. S. PRATAP	IA & IC Pvt Ltd, Bombay
SHRI C. N. VYAS (<i>Alternate</i>)	
SHRI N. M. REGE	All India Rubber Industries Association, Bombay
SHRI Y. S. LATHIA (<i>Alternate</i>)	
SHRI R. ROY CHOUDHURY	Phillips Carbon Black Ltd, Calcutta
DR S. P. BASU (<i>Alternate</i>)	
SHRI B. K. SEN CHAUDHURI	Escon Consultants Pvt Ltd, Calcutta
DR S. M. SHETTY	Canara Rubber Products Pvt Ltd, Mangalore
SHRI V. G. TORSEKAR	Polyolefine Industries Ltd, Bombay
SHRI V. K. SUD (<i>Alternate</i>)	
DR V. S. VIJAYAN NAYAR	Travancore Titanium Products Ltd, Trivandrum
SHRI D. V. WITTENBAKER	Waldiet Ltd, Calcutta
SHRI A. DEB (<i>Alternate</i>)	

INTERNATIONAL SYSTEM OF UNITS (SI UNITS)

Base Units

QUANTITY	UNIT	SYMBOL
Length	metre	m
Mass	kilogram	kg
Time	second	s
Electric current	ampere	A
Thermodynamic temperature	kelvin	K
Luminous intensity	candela	cd
Amount of substance	mole	mol

Supplementary Units

QUANTITY	UNIT	SYMBOL
Plane angle	radian	rad
Solid angle	steradian	sr

Derived Units

QUANTITY	UNIT	SYMBOL	DEFINITION
Force	newton	N	1 N = 1 kg.m/s ²
Energy	joule	J	1 J = 1 N.m
Power	watt	W	1 W = 1 J/s
Flux	weber	Wb	1 Wb = 1 V.s
Flux density	tesla	T	1 T = 1 Wb/m ²
Frequency	hertz	Hz	1 Hz = 1 c/s (s ⁻¹)
Electric conductance	siemens	S	1 S = 1 A/V
Electromotive force	volt	V	1 V = 1 W/A
Pressure, stress	pascal	Pa	1 Pa = 1 N/m ²