



Published 1976-08-15

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Rubber, isoprene (IR) — Non oil-extended, solution-polymerized types — Test recipe and evaluation of vulcanization characteristics

AMENDMENT 1 •

Amendment 1 to International Standard ISO 2303 was drawn up by Technical Committee ISO/TC 45, *Rubber and rubber products*. It was submitted directly to the ISO Council, in accordance with clause 6.12.1 of the Directives for the technical work of ISO.

RUBBER RESEARCH INSTITUTE
OF INDIA LIBRARY

Acc No 540

Date 23.2.83

Page 1

Sub-clause 3.1 : Replace the second note below the table by the following :

*** *N-Tert-butyl sulphenamide*. This shall be supplied in powder form having an initial ether- or ethanol-insoluble matter content of less than 0,3 % . The material shall be stored at room temperature in a closed container and the ether- or ethanol-insoluble matter shall be checked every 6 months. If this is found to exceed 0,75 %, the material shall be discarded or recrystallized."